

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>5</sup> : C08F 4/04, 4/34, 26/10</p>	<p>A1</p>	<p>(11) International Publication Number: <b>WO 94/18241</b> (43) International Publication Date: 18 August 1994 (18.08.94)</p>
<p>(21) International Application Number: PCT/US94/00806 (22) International Filing Date: 21 January 1994 (21.01.94) (30) Priority Data: 08/017,155 12 February 1993 (12.02.93) US (71) Applicant: ISP INVESTMENTS INC. [US/US]; 818 Washington Street, Wilmington, DE 19801 (US). (72) Inventors: WU, Chi-San; 12 Ashburn Road, Wayne, NJ 07470 (US). CURRY, James, F.; 51 Oakwood Drive, Wayne, NJ 07470 (US). CULLEN, James, P.; 209 Mattioli Drive, Bartonsville, PA 18360 (US). (74) Agents: MAUE, Marilyn, J. et al.; International Specialty Products, 1361 Alps Road, Wayne, NJ 07470 (US).</p>		<p>(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  Published With international search report.</p>
<p>(54) Title: FREE RADICAL SOLUTION POLYMERIZATION OF VINYLPIRROLIDONE (57) Abstract  A free radical solution process for making PVP polymers having a molecular weight corresponding to a K-value of about 30-150, a narrow molecular weight distribution represented by a polydispersity of about 3 to 6, and a residual VP monomer level of less than 0.1 %, which comprises: (a) precharging a reaction mixture of vinylpyrrolidone monomer and water in a solids contents w/w VP/H<sub>2</sub>O of about 5-50 %, and a dual free radical initiator system which comprises both low and high decomposition temperature free radical initiators whose 10-hour half-life temperature decomposition constants differ from each other by more than 5 °C, the low and high temperature initiators being present, respectively, in an amount of about 0.05-0.5 %, and about 0.1-0.5 %, by weight of the VP monomer, (b) polymerizing said monomer in said reaction mixture at a temperature near or above the 10-hour decomposition temperature of said low temperature initiator, and (c) after substantially all of the VP monomer has been converted to PVP polymer, continuing the polymerization at the same temperature as in (b), or at a higher temperature near or above the decomposition temperature of the high 10-hour temperature initiator, to complete the polymerization and to reduce the residual VP monomer level to less than 0.1 %.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

FREE RADICAL SOLUTION POLYMERIZATION  
OF VINYLPIRROLIDONE

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to free radical solution polymerization, and, more particularly, to polymerization of vinylpyrrolidone (VP) to polyvinylpyrrolidone (PVP) polymer using a predetermined initiator system to control the molecular weight (MW), the molecular weight distribution (MWD), and the residual VP monomer level of the PVP product.

2. Description of the Prior Art

Free radical solution polymerization is used widely in industry to prepare homopolymers and copolymers. See, for example, U.S. Patents 4,433,112; 4,554,311; 4,058,655; 4,053,696; 4,330,451; 3,862,915; and 4,886,861. In such process, the monomer, for example, vinylpyrrolidone, the solvent and the free radical initiator, are mixed and reacted at a selected temperature for a given period of time. Control of both the reaction temperature and viscosity of the reactants during the process has been considered essential in order to obtain a polymer of predetermined composition, MW, and viscosity, and having a narrow MWD.

It is also desired to carry out a free radical solution polymerization process so that the residual monomer content is quite low, preferably less than 0.1%.

Polymers having a low residual monomer content can be made by adding the initiator in stages, or continuously, during polymerization, or by providing a booster amount of the initiator in the final stage of the process. However, these techniques require rather complicated manufacturing procedures. Furthermore, the viscosity of the reaction mixture increases as polymerization proceeds; accordingly, it was difficult to intimately mix such successive portions of the initiator to the viscous mass which resulted in a localized high concentration of free radicals and a considerable variation in the MW, MWD and viscosity of the final product.

For these reasons, a single initiator is preferred in free radical solution polymerizations. Unfortunately, the resultant initiator concentration after 99% of the monomer has been converted to polymer is too low to effectively reduce the residual monomer level from 1% to less than 0.1%, and in a timely manner.

Accordingly, it is an object of this invention to provide a process for free radical solution polymerization of monomers to provide polymers of predetermined MW, a narrow MWD, a high viscosity, and a low residual monomer content.

A particular object herein is to provide a process for free radical solution polymerization of vinylpyrrolidone to polyvinylpyrrolidone having a K-value of about 30-150, an MWD of 3-6, and a residual monomer content of less than 0.1%.

These and other objects and features of the invention will be made apparent from the following more particular description.

SUMMARY OF THE INVENTION

What is provided herein is a free radical solution process for making PVP polymers having a molecular weight corresponding to a K-value of about 30-150, a narrow molecular weight distribution represented by a polydispersity of about 3 to 6, and a residual VP monomer level of less than 0.1%, which comprises:

(a) precharging a reaction mixture of vinylpyrrolidone monomer and water in a solids contents w/w VP/H<sub>2</sub>O of about 5-50%, and a dual free radical initiator system which comprises both low and high decomposition temperature free radical initiators whose 10-hour half-life temperature decomposition constants differ from each other by more than 5°C., the low and high temperature initiators being present, respectively, in an amount of about 0.05-0.5%, and about 0.1-0.5%, by weight of the VP monomer,

(b) polymerizing said monomer in said reaction mixture at a temperature near or above the 10-hour decomposition temperature of said low temperature initiator, and

(c) after substantially all of the VP monomer has been converted to PVP polymer, continuing the polymerization at the same temperature as in (b), or at a higher temperature near or above the decomposition temperature of the high 10-hour temperature initiator, to complete the polymerization and to reduce the residual VP monomer level to less than 0.1%.

DETAILED DESCRIPTION OF THE INVENTION

In this invention, the free radical polymerization process for making PVP homopolymers or copolymers allows for ease of temperature and viscosity control, reduces the residual monomer level to less than 0.1% without adding extra initiator in the final stage of polymerization, and is capable of making polymers with a uniform (narrow) MWD and a high bulk solution (Brookfield) viscosity. The important features of the process are as follows:

(1) The use of mixed low and high temperature initiators (two or more) with 10 hour half-life temperatures different from each other by at least several degrees. Two initiators are required, but more than two are also workable.

The primary function of the low temperature initiator is to produce a PVP polymer of a desired molecular weight; while the primary function of the high temperature initiator is to reduce the residual monomer level to less than 0.1%. The high temperature initiator remains "relatively dormant" as compared to the low temperature initiator in the beginning of the reaction, and becomes "dominant" in the final stage of the reaction, especially when the temperature is raised. This mixed initiator system thus precludes the problems overheating, drastic viscosity build-up, difficulty in removing residual monomer, previously associated with a single initiator polymerization system.

The amount of the low temperature initiator used in the mixed initiator system of the invention also is less than the amount of initiator used in a single initiator system to make polymers of similar MW and solids content.



(2) The dual mixture of a low and high temperature initiator can be added at the beginning of the polymerization. Final stage addition of the high temperature initiator is workable but is not necessary.

(3) The temperature of the reaction at the first stage is controlled to be close to or above the lowest of the 10-hour half-life temperatures of the initiator mixture. After the majority of the monomer has reacted, it is preferable, but not necessary, to increase the reaction temperature to close to or above the next lowest of the 10-hour half-life temperature of the initiator mixture to reduce the residual monomer level to less than 0.1%.

(4) The final residual monomer level can be reduced to less than 0.1% by holding the reaction mixture for a few hours or less in each of the two stages mentioned in (3).

(5) The uniform or narrow MWD of the polymer prepared in the mixed initiator system of the invention provides a polymer having a higher bulk solution (Brookfield) viscosity than prior polymers having the broad MWD value, at equivalent K-value (molecular weight) and concentration levels.

(6) Adjusting the ratio of the dual initiator mixture, and/or % solids, will provide polymers of different K-value (molecular weight) in the process of the invention.

(7) VP and other homopolymers and copolymers can be polymerized in water and organic solvents.

The invention will be described in more detail by reference to the following examples.

EXAMPLE 1

A 1-liter, 5-necked, jacketed glass reaction flask is equipped with a stirring shaft for mixing, a water-cooled condenser to prevent vapor loss, a thermocouple to monitor temperature, a rubber septum for introducing the initiators and for removing samples periodically, and a nitrogen sparge tube. The flask allows for a positive pressure of nitrogen to be maintained. Accordingly, nitrogen is bubbled through the reaction mixture for 20 minutes before starting the polymerization reaction.

The reaction mixture was prepared by mixing 169 g of vinylpyrrolidone (VP) and 599 g of distilled/deionized water to achieve a 22% (w/w) VP/H<sub>2</sub>O mixture. 0.02 g of EDTA was added and the mixture was stirred for 30 minutes to dissolve the EDTA. The pH of the mixture was 9.1. Then the mixture was added to the reaction flask.

The reaction mixture then was heated to 57°C. and 0.3% (v/w% of VP), 677 µl, of Lupersol 11\* (t-butylperoxy pivalate) initiator was added. Then 0.2% (v/w % of VP), 1.69 ml, of Vazo 67\*\* (2,2-azo(2-methyl butyronitrile)/VP mixture is added. The Vazo 67/VP mixture was prepared just before addition by adding 1 g of Vazo 67 to 4 g of VP and mixing for 1 minute. Then the temperature was controlled between 60 to 64°C. for two hours. Thereafter the temperature was increased to 80°C. and held for another 2 hours to complete the reaction. The polyvinylpyrrolidone (PVP) polymer product had a K-value of 74.7, a polydispersity of 3.2, a solids content of 22.4%, and residual VP content of only 0.06%.

\* Lupersol 11 - obtained as a 75% active solution of the initiator in mineral spirits from the Pennwalt Chemicals Division of NA Atochem (Phila, PA); 10-hour half-life,  $t_{1/2}$ , in trichloroethylene is 58°C.

\*\* Vazo 67 - obtained as a powder from duPont



EXAMPLE 2

The dual initiator procedure of Example 1 was followed using 0.125% (v/w % of VP) of Lupersol 11. The PVP obtained had a K-value of 91.3, a polydispersity of 4.6, a solids content of 23.8%, and a residual VP level of 0.08%.

EXAMPLE 3

The dual initiator procedure of Example 1 was followed using 0.1% (v/w % of VP) of Lupersol 11. The PVP obtained had a K-value of 94.4, a polydispersity of 4.6, a solids content of 22.7%, and a residual VP level of 0.07%.

EXAMPLE 4

The dual initiator procedure of Example 1 was followed using 0.06% (v/w % of VP) of Lupersol 11, and 182 g of deionized water was added after 2 hours before raising the temperature to 80°C. to reduce viscosity. The PVP product obtained had a K-value of 101.3, a polydispersity 4.8, a solids content of 18.9%, and a residual VP level of 0.07%.

EXAMPLES 5-9

The dual initiator procedure of Example 1 is followed using the following combinations of low and high temperature initiators to produce PVP having similar K-values, polydispersity and residual monomer levels as obtained for the Lupersol 11/Vazo 67 system.

DUAL INITIATOR POLYMERIZATIONS

Example	Low Temp.		10-hour Half-life		1st Stage Reaction		High Temp.		10-Hour Half-Life		2nd Stage Reaction	
	Initiator	Temp (°C.)	Temp (°C.)	Temp (°C.)	Temp (°C.)	Temp (°C.)	Initiator	Temp (°C.)	Temp (°C.)	Temp (°C.)	Temp (°C.)	Temp (°C.)
5	Lupersol 11	58	58	63	63	63	Vazo 88	88	88	88	95	95
6	Lupersol 11	58	58	63	63	63	Lupersol 80	82	82	82	92	92
7	Lupersol 11	58	58	63	63	63	Lupersol 575	75	75	75	85	85
8	Vazo 67	67	67	70	70	70	Vazo 88	88	88	88	95	95
9	Vazo 52	52	52	55	55	55	Vazo 67	67	67	67	80	80

## WHAT IS CLAIMED IS:

1. A free radical solution process for making PVP polymers having a molecular weight corresponding to a K-value of about 40-150, a narrow molecular weight distribution represented by a polydispersity of about 3 to less than 6, and a residual VP monomer level of less than 0.1%, which comprises:

(a) precharging a reaction mixture of vinylpyrrolidone monomer and water in a solids contents w/w VP/H<sub>2</sub>O of about 5-50%, and a dual free radical initiator system which comprises both low and high decomposition temperature free radical initiators whose 10-hour half-life temperature decomposition constants differ from each other by more than 5°C., the low and high temperature initiators being present, respectively, in an amount of about 0.05-0.5%, and about 0.1-0.5%, by weight of the VP monomer,

(b) polymerizing said monomer in said reaction mixture at a temperature near or above the 10-hour decomposition temperature of said low temperature initiator, and

(c) after substantially all of the VP monomer has been converted to PVP polymer, continuing the polymerization at the same temperature as in (b), or at a higher temperature near or above the decomposition temperature of the high 10-hour temperature initiator, to complete the polymerization and to reduce the residual VP monomer level to less than 0.1%.

2. A process according to claim 1 wherein said low temperature initiator is t-butylperoxy pivalate, and said high temperature initiator is 2,2-azo(2-methyl-butyronitrile).

3. A process according to claim 1 wherein (c) is carried out at a higher temperature near or above the 10-hour half-life temperature of the higher temperature initiator.

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US94/00806

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : C08F 4/04, 4/34, 26/10

US CL : 526/219.2, 227, 264

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 526/219.2, 227, 264

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,554, 312 (BARABAS ET AL.) 19 NOVEMBER 1985, Abstract.	1-3
Y	GB, A, 1,021,121 (GENERAL ANILINE & FILM CORPORATION) 23 FEBRUARY 1966, TABLE II.	1-3

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

*A*	document defining the general state of the art which is not considered to be part of particular relevance	*T*	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*E*	earlier document published on or after the international filing date	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*L*	document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*O*	document referring to an oral disclosure, use, exhibition or other means	*Z*	document member of the same patent family
*P*	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

04 APRIL 1994

Date of mailing of the international search report

MAY 12 1994

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

JOSEPH L. SCHOFER

Telephone No. (703) 308-2351